Film Structure

(BIAXIALLY ORIENTED POLYESTER FILM)

TECHNICAL DATA SHEET

Product Description:

F-ESB is a transparent polyester film

It has one side special modified functional surface and other side untreated or primer coated (AUU/ATU)

Application:

Printing & Iamination


Bag & pouch

Key Features:

Very good clarity & transparency

Excellent machinability & handling properties One side special modified functional surface for stacking of bags to prevent from slippage in storage or palletization

Primer coating on other side provide excellent adhesion with inks & adhesives



PROPERTIES		TEST METHOD (ASTM)	UNIT	TYPICAL VALUE	
				12	23
THICKNESS		Internal	Micron	12	23
			(Gauge)	48	92
FILM DENSITY		D-1505	gm/cc	1.4	1.4
GRAMMAGE		Internal	gm/m ²	16.8	32.2
YIELD		Internal	m ² /kg	59.52	31.05
			in²/lb	41934	21876
TREATMENT LEVEL # (Primer coated Side) AUU/ATU COEFF OF KINETIC FRICTION	(Min)	D-2578	dyne/cm	42 / 52	42/52
(Modified side to modified side)	(Min)	D-1894	-	0.80	0.80
(Other side to other side)	(Max)			0.45	0.45
HAZE		D-1003	%	1.5	2.0
TENSILE STRENGTH AT BREAK	MD*	D-882	Kg/cm ²	1900	1900
TENSILE STRENGTH AT BREAK ELONGATION AT BREAK	TD*			2000	2000
	MD*		(Psi)	27000	27000
	TD*			28500	28500
	MD	D-882	%	105	115
	TD			85	90
LINEAR SHRINKAGE (Max.)	MD	D-1204	%	3.0	3.0
(30 Minute at 150 ⁰ C)	TD			1.0	1.0
W.V.T.R.(38 ⁰ C & 90%RH)		F-1249	gm/m²/day	45	30
			(gm/100in²/day)	2.9	2.0
O.T.R. (23 ⁰ C & 0%RH)		D-3985	cc/m²/day	130	80
			(cc/100in²/day)	8.5	5.2

Ref no QAD UFLLS/10 - F25/1

STORAGE & HANDLING:

FLEXPET[™] need to be stocked in a closed warehouse and should not be exposed to direct sunlight or light sources and from humidity. It is recommended to store below 35°C in dry place. FLEXPET™ is suitable for use within 9 month from date of manufacturing, only if material is stored in recommended condition.

FOOD CONTACT:

FLEXPET[™] complies with EC and FDA regulations. Specific document and MSDS are available on request.

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.

^{*}MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

[#] The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm