

**Product Description:**

FLEXMETPROTECT™ F-PAB-M is a metallized polyester film having metallization on corona side and other side chemically coated surface.

Key Features:

Improved Barrier properties
Balance mechanical properties in all direction
Excellent Machinability & handling properties

Applications:

Balloon application

FLEXMETPROTECT™ F-PAB-M grade of film is metallized polyester film. The film have superior gloss when metallized on optically clear base film and further improved when metallized on extra clear base film. The film is one side proprietary coated layer whereas other side is corona treated. Film is available in optical density ranging from 2.0 to 3.0. The wide range of optical densities give choice to the customer to use the product for diverse range of applications. The metallization is available on corona treated side (MT) . The bond between the metal & film is 130-180 gms/25mm (when metallized on corona side), Film is suitable for Balloon application.

PROPERTIES	TEST METHOD (ASTM)	UNIT	TYPICAL VALUE	
				9
OPTICAL DENSITY (TOLERANCE : +/- 5%)		-		2.8
THICKNESS	Internal	Micron		9
		(Gauge)		36
FILM DENSITY	D-1505	gm/cc		1.4
GRAMMAGE	Internal	gm/m ²		12.6
YIELD	Internal	m ² /kg		79.36
		in ² /lb		55912
COEFF OF KINETIC FRICTION	D-1894	-		0.7
METAL WOUND				#MI/MO
TENSILE STRENGTH AT BREAK	MD*	D-882	Kg/cm ²	2300
	TD*			2500
	MD*		(Psi)	32700
	TD*			35500
ELONGATION AT BREAK	MD	D-882	%	100
	TD			80
LINEAR SHRINKAGE (Max.) (AT 105 ^o C/30 Minute)	MD	D-1204	%	1.5
	TD			0.6
W.V.T.R.(38 ^o C & 90%RH)	F-1249	gm/m ² /day		0.4
		(gm/100in ² /day)		0.03
O.T.R. (23 ^o C & 0%RH)	D-3985	cc/m ² /day		0.8
		(cc/100in ² /day)		0.05

Ref no QAD UFLI S/16 - MF19 /1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

MI = Metal wound inside, MO = Metal wound out side

STORAGE & HANDLING

FLEXMETPROTECT™ need not to be stocked in a closed warehouse and should not be exposed to direct sunlight or light sources and from humidity. It is recommended to store below 35° C in dry place. FLEXMETPROTECT™ is suitable for use within 6 months from date of manufacturing, only if stored in recommended condition.

FOOD CONTACT

FLEXMETPROTECT™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.

**TDS issued on 27-05-2016.

Website: www.flexfilm.com