

Product Description:

F-TFP is a Co-extruded transparent polyester film . It is one side corona treated or both side untreated. Film is specially designed for shallow draw thermoforming applications. Film is recommended to be laminated with a sealant layer.

Applications:


Trays, packs and lids

Fresh and frozen food applications

Key Features:

Very good clarity & transparency

One side corona treatment provides good adhesion with inks

Film Structure


PROPERTIES	TEST METHOD (ASTM)	UNIT	TYPICAL VALUE				
			15	19	23	36	
THICKNESS	Internal	Micron (Gauge)	15 60	19 76	23 92	36 144	
FILM DENSITY	D-1505	gm/cc	1.4	1.4	1.4	1.4	
GRAMMAGE	Internal	gm/m ²	21.0	26.6	32.2	50.4	
YIELD	Internal	m ² /kg in ² /lb	47.62 33550	37.59 26483	31.05 21876	19.84 13978	
TREATMENT LEVEL # Corona treated Side (Min)	D-2578	dyne/cm	52	52	52	52	
COEFF OF KINETIC FRICTION ((Corona treated to Untreated Side) (Untreated to Untreated side)	D-1894	-	0.50 0.45	0.50 0.45	0.45 0.40	0.45 0.40	
HAZE (Max)	D-1003	%	4.0	4.0	4.5	5.0	
TENSILE STRENGTH AT BREAK	D-882	Kg/cm ² (Psi)	MD* TD*	1900 2000	1900 2000	1900 2000	1750 2000
TENSILE STRENGTH AT BREAK			MD* TD*	27000 28500	27000 28500	27000 28500	25000 28500
ELONGATION AT BREAK			MD TD	≥ 200 95	≥ 200 100	≥ 200 110	≥ 200 120
LINEAR SHRINKAGE (30 Minute at 150°C)			MD TD	7.0 3.0	7.0 3.0	7.0 3.0	7.0 3.0
W.V.T.R.(38°C & 90%RH)	F-1249	gm/m ² /day (gm/100in ² /day)	40 2.6	35 2.3	30 2.0	20 1.3	
O.T.R. (23°C & 0%RH)	D-3985	cc/m ² /day (cc/100in ² /day)	110 7.1	90 5.8	80 5.2	70 4.5	

Ref no QAD UFLI S/16 -F58/1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

STORAGE & HANDLING:

FLEXPET™ need to be stocked in a closed warehouse and should not be exposed to direct sunlight or light sources and from humidity. It is recommended to store below 35°C in dry place. FLEXPET™ is suitable for use within 9 month from date of manufacturing, only if material is stored in recommended condition.

FOOD CONTACT:

FLEXPET™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER:

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information.

**TDS issued on 07-10-2017. All previous version of this grade are invalid.

Website: www.flexfilm.com