

TECHNICAL DATA SHEET
Product Description:

F-WCH is a white opaque polyester film

It is one side chemical coated or other side untreated

Application:

Surface printing jobs & metallization

Label application & blister packaging

Other conversion where white backing required like lids


Key Features:

Excellent opacity & high brightness

Excellent machinability & handling properties

Good mechanical & thermal properties

Chemical coated side provide excellent bonding with various inks & adhesive

Film Structure


PROPERTIES	TEST METHOD (ASTM)	UNIT	TYPICAL VALUE		
			23	36	50
THICKNESS	Internal	Micron (Gauge)	23 92	36 144	50 200
FILM DENSITY	D-1505	gm/cc	1.45	1.45	1.45
GRAMMAGE	Internal	gm/m ²	33.4	52.2	72.5
YIELD	Internal	m ² /kg in ² /lb	29.98 21122	19.16 13499	13.79 9715
TREATMENT LEVEL # (Chemical coated side)	(Min) D-2578	dyne/cm	60	60	60
COEFF OF KINETIC FRICTION (Untreated to untreated)	(Max) D-1894	-	0.45	0.45	0.45
OPACITY	(Min.) D-2457	%	75	82	85
TENSILE STRENGTH AT BREAK	MD*	Kg/cm ²	1600	1500	1500
	TD*		2000	2000	2000
TENSILE STRENGTH AT BREAK	MD*	(Psi)	22700	21300	21300
	TD*		28500	28500	28500
ELONGATION AT BREAK	MD	%	115	120	125
	TD		80	85	90
LINEAR SHRINKAGE (Max.) (30 Minute at 150 ⁰ C)	MD TD	D-1204		2.5 0.8	

Ref no. QAD UFLD S/10 - F24/1

*MD = MACHINE DIRECTION *TD = TRANSVERSE DIRECTION

The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

STORAGE & HANDLING:

FLEXPET™ need to be stocked in a closed warehouse and should not be exposed to direct sunlight or light sources and from humidity. It is recommended to store below 35°C in dry place. FLEXPET™ is suitable for use within 9 month from date of manufacturing, only if material is stored in recommended condition.

FOOD CONTACT:

FLEXPET™ complies with EC and FDA regulations. Specific document and MSDS are available on request.

DISCLAIMER:

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information

**TDS issued on 11-02-2015. All previous version of this grade are invalid.

Website: www.flexfilm.com